

Shield your muzzleloader (and scope) from itself.

Dyna-Gun Shield

Superior protection, hand applied and environmentally friendly.
Did we mention there's no catch?

- CAN BE HAND-APPLIED AT HOME
Dyna-Gun Shield is the only hand-applied clear coating offered in the firearms industry. You can wipe, dip or spray it on **in the comfort of your home.**
- HARDEST CLEAR COAT AVAILABLE IN THE FIREARMS INDUSTRY
Dyna-Gun Shield will provide a 6h hardness if air-dried, and with a 350° F bake you will see 7h to 9h!
- ENVIRONMENTALLY FRIENDLY
Dyna-Gun Shield has no ozone-depleting V.O.C.s.



- GREAT CORROSION RESISTANCE
The outdoors, propellants, cleaning chemicals and the blast from your gun will ruin the finish on your muzzleloader. Dyna-Gun Shield shrugs off MEK, paint strippers, cleaning agents and blowback.
- OPTICAL CLARITY
Dyna-Gun Shield goes on completely clear over your muzzleloader's finish ... you won't even know it's there.
- NANO-TECHNOLOGY MEANS EXCELLENT ADHESION
Dyna-Gun Shield can be applied over blued, camouflaged, or anodized surfaces to protect the finish.
- AIR-DRY FINISH
There's no heat required to cure the coating (but it loves heat too; the coating is good up to 1,800°).

5000 E. 59th St., Kansas City, MO 64130

Tel 816.444.1255 x 110 Fax 816.423.8125

E-mail: info@dynacoatings.com

Buy it at: www.ultracoatingsinc.com/cart.aspx

WANT MORE?

HERE ARE MORE
OPTIONS FOR YOUR
COATING.

• **WET GRIP**

This unique chemistry gives the coatings grip-ability when you perspire or get your firearm wet.

• **SOFT-TOUCH**

Want that permanent rubber-like grip but still hard as heck? Ask for Dyna-Soft Touch. (This option must be sprayed on.)

• **TO GLOSS OR NOT TO GLOSS**

Want high gloss? Satin, matte or no gloss? Just ask!



Before and after: scope coated with Dyna-Gun Shield after 1,000 rounds.



Dyna-Gun Shield is easy
to hand-apply at home!

*Physical properties will increase with elevated temperature and pressure cure cycles (the more you shoot it, the better it gets).

Color	Clear or Matte Clear
Odor	Slight Solvent
V.O.C.	0.0%-No Ozone Depleting Chemicals
Salt Spray (5% Solution)	850 Hours (ambient cure)*
Pencil Hardness	6h (ambient cure)* (ASTM D 3363)
Conical Bend @ 1/8 Mandrel	No Loss (ASTM D522-93a)
Cross-Cut Adhesion	5B



5000 E. 59th St., Kansas City, MO 64130

Tel 816.444.1255 x 110 Fax 816.423.8125

E-mail: info@dynacoatings.com

Buy it at: www.ultracoatingsinc.com/cart.aspx